



Coru166 Blue Food Quality Nitrile Rubber 60° shore

Approved to: FDA 21 CFR No: 177 – 2600 – EU1935/2004 regulations and USP Class V1 Compliant

PROPERTIES	TEST METHOD	VALUES FPS UNITS	TEST METHOD	VALUES METRIC UNITS
SPECIFIC GRAVITY	ASTM D297	1.40 ± 0.05	DIN 53508	1.40 ± 0.05
HARDNESS	ASTM D2240	60 ± 5 SH A	DIN 53505	60 ± 5 SH A
TENSILE STRENGTH (MIN)	ASTM D412	1140 PSI	DIN 53504	60 KG/CM2
ELONGATION AT BREAK (MIN)	ASTM D412	350%	DIN 53504	350%
COMPRESSION SET (70 °C/24 HRS/25% SET) (MAX)	ASTM D395 METHOD B	40%	DIN 53517	40%
TEAR RESISTANCE (ANGULAR) MIN	ASTM D624	112 LBS/INCH	DIN 53515	20 KG/CM
CHANGE IN PROPERTIES				
HEAT AGEING (72 HRS. AT 70 °C)	ASTM D573			
--- HARDNESS (PTS)		+ 4 (MAX)		+ 4 (MAX)
--- TENSILE STRENGTH (%)		+ 10 / - 15		+ 10 / - 15
--- ELONGATION AT BREAK (%)		+ 10 / - 20		+ 10 / - 20
VOLUME SWELL : AT 70° C FOR 72 HRS/IN	ASTM D 471			
ASTM OIL NO.1		+ 3 %		+ 3 %
ASTM OIL NO.2		+ 16%		+ 16%
ASTM OIL NO.3		+ 20%		+ 20%
POLYMER CONTENT (NITRILE)		100%		100%
CHEMICAL RESISTANCE				
--- OZONE	ASTM D 1149	FAIR		FAIR
--- DILUTE ACIDS AND BASES		GOOD		GOOD
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- OILS		GOOD		GOOD
--- SOLVENTS		FAIR		FAIR
TEMPERATURE RANGE		-25° TO + 110° C		-25° TO + 110° C
COLOUR		RAL 5012 BLUE		RAL 5012 BLUE
POLYMER CONTENT (%)		100		

Test Name – Determination of Amount of extractives

Method : With reference to US FDA 21 CFR 177.2 00

Extractants	Test Condition	Amount of Extractives mg/inch ²	Acceptable limit mg/inch ²	Conclusion
		1		
Distilled Water	70 °C for 2 hours	10	20	Pass
n-Hexane	70 °C for 2 hours	100	175	Pass

Note:

1. mg/inch² denotes Milligram per square inch
2. °C denotes Degrees Celsius