



Coru193 – Black Nitrile to BS2751 BA80

PROPERTIES	TEST METHOD	VALUES
		METRIC UNITS
DENSITY (Mg/m3)	BS 903: PART A1	1.25 ± 0.02
HARDNESS	BS903: PART A26	80 (+5-4) IRHD
TENSILE STRENGTH (MIN)	BS 903: PART A2	12.5 Mpa
ELONGATION AT BREAK (MIN)	BS 903: PART A2	150%
COMPRESSION SET (70°C/24 HRS/25% SET) (MAX)	BS 903: PART A6	20%
TEAR RESISTANCE (ANGULAR) MIN	BS 903: PART A3	55 Kg/cm
RESISTANCE TO ACCELERATED AGEING – 168 HRS AT 70°C	BS 903: PART A19	
--- HARDNESS (Pts)	BS 903: PART A26	+ 10 (MAX)
--- TENSILE STRENGTH (%)	BS 903: PART A2	-10 (MAX)
--- ELONGATION AT BREAK (%)	BS 903: PART A2	-35 (MAX)
VOLUME SWELL : AT 40°C FOR 24 HRS/IN	BS 903: PART A16	
FUEL B (MAX)		+25%
RESISTANCE TO LOW TEMPERATURE IN °C AT WHICH THE STIFNESS SHALL NOT EXCEED 70 MPA	BS 903: PART A13	-15
ADHESION TO AND CORROSION OF METALS AT 70°C / 168 HRS	BS 903: PART A 37	MEETS REQUIREMENTS
POLYMER CONTENT (NITRILE)		100%
ADDITIONAL INFORMATION -		
CHEMICAL RESISTANCE		
--- OZONE	BS 903: PART A 43	FAIR
--- DILUTE ACIDS AND BASES	BS 903: PART A16	GOOD
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED
--- MINERAL OIL/PETROLEUM		EXCELLENT
--- SOLVENTS		FAIR
TEMPERATURE RANGE		-10° to +120°C
COLOUR		BLACK
VOLUME SWELL: AT 70 C FOR 72 HRS/IN		VALUES
IRM / ASTM OIL NO.1		- 3 %
IRM / ASTM OIL NO.2		- 2%
IRM / ASTM OIL NO.3		+ 10%